

The tables below describe all the technical specifications for barpa fiber. Complies the standards ISO11801 and EN50173-1. If you have any special request for fiber please contact our team, we are glad to find a solution for your needs.

FOR MULTIMODE:

Optical Performance	Conditions	OM2	OM3	OM4	OM5
Attenuation (dB/km)	850nm	≤ 2,7	≤ 3,0	≤ 3,0	≤ 3,0
	953nm	-	-	-	≤ 2,3
	1300nm	≤ 0,8	≤ 1,0	≤ 1,0	≤ 1,0
Bandwidth (MHz.km)	850nm	≥ 500	≥ 1500	≥ 3500	≥ 3500
	953nm	-	-	-	≥ 1850
	1300nm	≥ 500	≥ 500	≥ 500	≥ 500
Effective Modal Bandwidth (MHz.km)	850nm	-	≥ 2000	≥ 4700	≥ 4700
	953nm	-	-	-	≥ 2470
Numerical Aperture			0,200 ± 0,015		
Effective Group Index of Refraction	850nm		1,482		
	1300nm		1,477		

Geometrical Data	OM2	OM3	OM4	OM5
Core Diameter (µm)		50,0 ± 2,5		
Core Non-Circularity (%)		≤ 5,0		
Core / Cladding Concentricity error (µm)	≤ 1,0	≤ 1,0	≤ 1,0	≤ 1,0
Cladding Diameter (µm)		125,0 ± 1,0		
Cladding Non-Circularity (%)		≤ 0,7		
Overall coating Diameter (µm)		250 ± 15		
Coating/Clad concentricity error (µm)		≤ 10		

Mechanical Characteristics	OM2	OM3	OM4	OM5
Proof Stress Level (GPa)		≥ 0,7 (1%)		
Coating Strip Force (typical) (N)		1,3 ≤ F _{peak.strip} ≤ 8,9		

Transmission Distance	OM3	OM4	OM5
10GBASE-SR	300m	550m*	550m*
40GBASE-SR4	140m*	190m*	190m*
100GBASE-SR10	140m*	-	-
25GBASE-SR	-	100m	100m
100GBASE-SR4	70m	100m	100m
400GBASE-SR4.2	-	100m	150m
40G-BiDi	-	150m	200m
100G-BiDi	-	100m	150m
40G SWDM4	-	350m	440m
100G SWDM4	-	100m	150m

*Indicated link distances require total connector loss ≤ 1.0 dB, and VCSEL spectral bandwidth of ≤ 0.45 nm

This document is authored and owned by barpa. It is forbidden to reproduce in whole or in part without mentioning its authorship, as well as modification of its content or context. All specifications are subject to change without notice. The pictures/drawings are merely illustrative.

More information: info@barpa.eu or in www.barpa.eu

datasheet n° b49_5 | date: 11/23

approved by: Ana Barbosa

FOR SINGLEMODE:

Optical Performance	Conditions	G652D	G657A2	G657B3
Attenuation (dB/km)	1310nm	≤ 0,39	≤ 0,38	≤ 0,36
	1383nm	≤ 0,39	≤ 0,38	≤ 0,36
	1550nm	≤ 0,25	≤ 0,23	≤ 0,22
	1625nm	≤ 0,25	≤ 0,25	≤ 0,25
Dispersion Coefficient (ps/km.nm)	1285 para 1330nm	≤ 3	≤ 3,7	≤ 3,7
	1550nm	≤ 18	≤ 18,5	≤ 18,5
	1625nm	≤ 22	≤ 23	≤ 23
Mode Field Diameter (μm)	1310nm	9,00 ± 0,40	8,80 ± 0,40	8,80 ± 0,40
	1550nm	10,10 ± 0,50	9,80 ± 0,50	9,80 ± 0,50
Effective Group Index of Refraction	1310nm	1,467	1,467	1,467
	1550nm	1,468	1,467	1,467
	1625nm	1,468	1,468	1,468
Zero Dispersion Wavelength λ _o (nm)		1300 < λ _o < 1322	1300 < λ _o < 1324	1300 < λ _o < 1324
Zero Dispersion Slope, S _o (ps/nm ² .km)		≤ 0,090	≤ 0,092	≤ 0,092
Cable Cutoff Wavelength λ _{cc} (nm)			≤ 1260	

Geometrical Data	G652D	G657A2	G657B3
Cladding Diameter (μm)		125 ± 0,7	
Cladding Npn-Circularity (%)		≤ 0,70	
Coating Diameter (μm)		242 ± 7	
Coating / Cladding Concentricity error (μm)		≤ 12,0	
Coating Non-Circularity (%)	≤ 5,0	≤ 7,0	≤ 6,0
Core / Cladding Concentricity error (μm)		≤ 0,5	

Mechanical Characteristics	G652D	G657A2	G657B3
Proof Test (GPa)		≥ 0,7	
Strip Force (N)		1,2 ≤ F _{peak.strip} ≤ 8,9	
Dynamic Fatigue	≥ 20	≥ 20	≥ 27

MACROBEND LOSS FOR SINGLEMODE:

• G652D

	Diameter of mandrel	Turns	Wavelength	Inducted Attenuation (dB)
Macrobend Loss	φ25mm	100 turns	1310nm e 1550nm	≤ 0,05
	φ30mm	100 turns	1625nm	≤ 0,05

• G657A2

	Diameter of mandrel	Turns	Wavelength	Inducted Attenuation (dB)
Macrobend Loss	φ15mm	10 turns	1550nm	≤ 0,03
	φ15mm	10 turns	1625nm	≤ 0,1
	φ10mm	1 turn	1550nm	≤ 0,1
	φ10mm	1 turn	1625nm	≤ 0,2
	φ7.5mm	1 turn	1550nm	≤ 0,5
	φ7.5mm	1 turn	1625nm	≤ 1,0

• G657B3

	Diameter of mandrel	Turns	Wavelength	Inducted Attenuation (dB)
Macrobend Loss	φ15mm	10 turns	1550nm	≤ 0,03
	φ15mm	10 turns	1625nm	≤ 0,10
	φ10mm	1 turn	1550nm	≤ 0,03
	φ10mm	1 turn	1625nm	≤ 0,10
	φ7.5mm	1 turn	1550nm	≤ 0,08
	φ7.5mm	1 turn	1625nm	≤ 0,20
	φ5mm	1 turn	1550nm	≤ 0,10
	φ5mm	1 turn	1625nm	≤ 0,30