




## Test Report

**Report No.** THJS17113012605-EN

**Date:** Dec. 08, 2017

Applicant : barpa  
Address : Zona Industrial da Portelinha Rua Noé Pereira, 473, 4510-706  
Fânzeres-GONDOMAR  
Sample Name : Fiber Pigtail  
813N1TTCCM (N refer to conector, TT refer to category, CC refer to  
Tested Model : color and M refer to meter)  
Sample Receiving date : 2017-12-05  
Test period : 2017-12-05 – 2017-12-08  
Test Requirement : The Restriction of the Use of Certain Hazardous Substances  
in Electrical and Electronic Equipment, 2011/65/EU.  
Test Method : Please refer to next page(s).  
Test result : Please refer to next page(s).  
Conclusion : **PASS**  
Based on the verification results of the submitted sample(s), the results of  
Lead, Cadmium, Mercury, Hexavalent chromium, Polybrominated  
biphenyls (PBBs) and Polybrominated diphenyl ethers (PBDEs) comply  
with the limits as set by RoHS Directive 2011/65/EU—The Restriction of  
the Use of Certain Hazardous Substances in Electrical and Electronic  
Equipment.  
Note : The test results are related only to the tested items.

Authorized Signature

*For and on behalf of*  
Shanghai Global Testing Services Co., Ltd.  
  
Shi Lei/Kevin  
General Manager -GTS/SHO



Page 1 of 6

This document is issued subject to GTS GENERAL CONDITIONS OF SERVICE, and shall not be reproduced except in full or with written approval by GTS Testing.

Shanghai Global Testing Services Co., Ltd.

No.968 Meilong West Road, Minhang District, Shanghai, 201104 China

Tel: (86-21) 3363 7866 Fax: (86-21) 3363 7858 E-mail: info@gts-lab.com Web Site: <http://www.gts-lab.com>



## Test Report

**Report No.** THJS17113012605-EN

**Date:** Dec. 08, 2017

### **Test Method:**

1. Disassembly, disjointment and mechanical sample preparation
  - Ref. to IEC 62321-2: 2013, Disassembly, disjointment and mechanical sample preparation.
2. With reference to IEC 62321-1: 2013, tests were performed for the samples indicated by the photos in this report.
  - (1) Screening – Lead, mercury, cadmium, total chromium and total bromine
    - Ref. to IEC 62321-3-1: 2013, Screening for Lead, mercury, cadmium, total chromium and total bromine by X-ray fluorescence spectrometry.
  - (2) Wet chemical test method
    - a. Total Lead, Cadmium, Chromium and Mercury content
      - Ref. to IEC 62321-4: 2013, determination of Mercury in polymers, metals and electronics by ICP-OES.
      - Ref. to IEC 62321-5: 2013, determination of Cadmium, lead and chromium in polymers and electronics and cadmium and lead in metals by ICP-OES.
    - b. Chromium (VI) content
      - For Colourless and coloured corrosion-protected coatings on metals, Ref. to IEC 62321-7-1: 2015, determination of presence of hexavalent chromium (Cr(VI)) in colourless and coloured corrosion-protected coatings on metals by the colorimetric method.
      - For polymers and electronics, Ref. to IEC 62321-7-2: 2017, determination of hexavalent chromium (Cr(VI)) in polymers and electronics by the colorimetric method.
    - c. PBBs, PBDEs
      - Ref. to IEC 62321-6: 2015, determination of polybrominated biphenyls and polybrominated diphenyl ethers in polymers by gas chromatography -mass spectrometry (GC-MS).



## Test Report

Report No. THJS17113012605-EN

Date: Dec. 08, 2017

### Test result(s):

Part No.	Part Description	Results of EDXRF					Chemical confirmation results (mg/kg)	Conclusion
		Pb	Cd	Hg	Cr	Br		
1	Green plastic	BL	BL	BL	BL	IN	PBBs: N.D. PBDEs: N.D.	Pass
2	White plastic	BL	BL	BL	BL	IN	PBBs: N.D. PBDEs: N.D.	Pass
3	Silvery metal	BL	BL	BL	BL	---	---	Pass
4	Green rubber	BL	BL	BL	BL	BL	---	Pass
5	Transparent plastic	BL	BL	BL	BL	BL	---	Pass
6	Metal (spring)	BL	BL	BL	IN	---	Cr(VI): Negative	Pass
7	Transparent plastic	BL	BL	BL	BL	BL	---	Pass
8	Ceramic	BL	BL	BL	BL	---	---	Pass
9	Silvery metal	OL	BL	BL	BL	---	Pb: 18600 <sup>(^4)</sup> Cd: 12	Pass
10-1	Yellow plastic sheath	BL	BL	BL	BL	BL	---	Pass
10-2	Optical fiber	BL	BL	BL	BL	BL	---	Pass

## Test Report

**Report No.** THJS17113012605-EN

**Date:** Dec. 08, 2017

Remark:

(^1) “---” = Not Applicable;

(^2) (a) It is the result on total Br while test item on restricted substances is PBBs/PBDEs. It is the result on total Cr while test item on restricted substances is Cr(VI).

(b) The XRF screening test for RoHS elements-The reading may be different to the actual content in the sample be of non-uniformity composition.

(c) Results are obtained by EDXRF for primary screening, and further chemical testing by ICP-OES (for Pb, Cd, Hg), UV-VIS for Cr(VI) and GC/MSD (for PBBs/PBDEs) is recommended to be performed if the concentration exceeds the below warning value according to IEC 62321-3-1: 2013.

Attached table 1, XRF screening limits in mg/kg for regulated elements in various matrices:

Element	Polymer Materials	Metallic Materials	Electronics
Cd	$BL \leq (70-3\sigma) < X < (130+3\sigma) \leq OL$	$BL \leq (70-3\sigma) < X < (130+3\sigma) \leq OL$	$LOD < X < (250+3\sigma) \leq OL$
Pb	$BL \leq (700-3\sigma) < X < (1300+3\sigma) \leq OL$	$BL \leq (700-3\sigma) < X < (1300+3\sigma) \leq OL$	$BL \leq (500-3\sigma) < X < (1500+3\sigma) \leq OL$
Hg	$BL \leq (700-3\sigma) < X < (1300+3\sigma) \leq OL$	$BL \leq (700-3\sigma) < X < (1300+3\sigma) \leq OL$	$BL \leq (500-3\sigma) < X < (1500+3\sigma) \leq OL$
Br	$BL \leq (300-3\sigma) < X$	N.A.	$BL \leq (250-3\sigma) < X$
Cr	$BL \leq (700-3\sigma) < X$	$BL \leq (700-3\sigma) < X$	$BL \leq (500-3\sigma) < X$

Note: ① BL “below limit” = the result less than the limit.

② OL “over limit” = the result greater than the limit.

③ IN = inconclusive, the region where need further chemical testing by ICP-OES (for Pb、Cd、Hg), UV-VIS (for Cr(VI)) and GC/MSD (for PBBs, PBDEs).

④  $3\sigma$  = Repeability of the analyser at the action level.

⑤ LOD = Limit of detection.

(^3) (a) mg/kg = ppm = 0.0001%;

(b) N.D. = Not detected (lower than RL);

(c) Reporting Limit (RL) and Limit of Directive 2011/65/EU.

Parameter	Unit	Limit	Reporting Limit (RL)
Lead (Pb)	mg/kg	1000	10
Cadmium (Cd)	mg/kg	100	10
Mercury (Hg)	mg/kg	1000	10
Chromium VI (Cr VI)	mg/kg	1000	R1
Group PBBs	mg/kg	1000	R2
Group PBDEs	mg/kg	1000	R2



## Test Report

Report No. THJS17113012605-EN

Date: Dec. 08, 2017

R1: Cr(VI) for metal sample, the reporting limit (RL)= Method Detection Limit (MDL)=0.10 ug/cm<sup>2</sup>.

The reporting limit (RL) of Cr(VI) for polymers and electronics is 10mg/kg.

R2: The reporting limit (RL) for single compound of PBBs & PBDEs is 50mg/kg.

(d) According to IEC 62321-7-1: 2015, result on Cr(VI) for metal sample is shown as Negative, Inconclusive or Positive: Negative = Absence of Cr(VI), Inconclusive = Maybe exist Cr(VI), Positive = Presence of Cr(VI).

Colorimetric result (Cr(VI) concentration)	Qualitative result
The sample solution is < the 0.10 ug/cm <sup>2</sup> equivalent comparison standard solution	The sample is negative for Cr(VI)-The Cr(VI) concentration is below the limit of quantification. The coating is considered a non-Cr(VI) based coating.
The sample solution is ≥ the 0.10 ug/cm <sup>2</sup> and ≤ the 0.13 ug/cm <sup>2</sup> equivalent comparison standard solutions	The result is considered to be inconclusive – Unavoidable coating variations may influence the determination. Recommendation: if addition samples are available, perform a total of 3 trials to increase sampling surface area. Use the averaged result of the 3 trials for the final determination.
The sample solution is > the 0.13 ug/cm <sup>2</sup> equivalent comparison standard solution	The sample is positive for Cr(VI)-The Cr(VI) concentration is above the limit of quantification and the statistical margin of error. The sample coating is considered to contain Cr(VI).


(^4) According to the declaration from the client, Lead (Pb) was exempted by EU RoHS Directive 2011/65/EU based on Annex III 6(c): Copper alloy containing up to 4% lead by weight.

## Test Report

Report No. THJS17113012605-EN


Date: Dec. 08, 2017

Sample photo(s):



Test item: Fiber Pigtail

Tested Model: 813N1TTCCM (N refer to conector, TT refer to category, CC refer to color and M refer to meter)



\*\*\*\*End of Report\*\*\*\*